











INFORMAZIONI TECNICHE

TECHNICAL FEATURES / INFORMATIONS TECHNIQUES / TECHNISCHE INFORMATIONEN / INFORMACIÓN TÉCNICA

DESCRIZIONE DESCRIPTION / DESCRIPTION BESCHREIBUNG / DESCRIPCIÓN	NORME REGULATION / NORME / NORM / NORMA EN 14411 - ISO 13006	REQUISITI PRESCRITTI REQUIRED VALUES / EXIGENCES RÉGLEMENTAIRES / VORGE- SCHRIEBENE ANFORDERUNGEN / REQUISITOS ESTABLECIDOS	VALORI VALUES / VALEURS WERTE / VALORES CEMENTINE	
 DIMENSIONI RETTIFICATO SIZES RECTIFIED / FORMAT RECTIFIÉ / ABMESSUNGEN NACH DEM SCHLEIFEN / TAMAÑO RECTIFICADO	UNI EN ISO 10545-2	lunghezza-larghezza $\pm 0,3\%$ ($\pm 1,0$ mm max) <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i>	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME	
		spessore $\pm 5,0\%$ ($\pm 0,5$ mm max) <i>thickness / épaisseur / Stärke / espesor</i>		
		ortogonalità $\pm 0,3\%$ ($\pm 1,5$ mm max) <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i>		
		rettilinearità $\pm 0,3\%$ ($\pm 0,8$ mm max) <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i>		
 DIMENSIONI NON RETTIFICATO SIZES NOT RECTIFIED / FORMAT NON RECTIFIÉ / ABMESSUNGEN VOR DEM SCHLEIFEN / TAMAÑO NO RECTIFICADO	UNI EN ISO 10545-2	lunghezza-larghezza $\pm 0,6\%$ ($\pm 2,0$ mm max) <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i>	-	
		spessore $\pm 5,0\%$ ($\pm 0,5$ mm max) <i>thickness / épaisseur / Stärke / espesor</i>		
		ortogonalità $\pm 0,5\%$ ($\pm 2,0$ mm max) <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i>		
		rettilinearità $\pm 0,5\%$ ($\pm 1,5$ mm max) <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i>		
 ASSORBIMENTO ACQUA WATER ABSORPTION / ABSORPTION D'EAU / WASSERAUFNAHME / ABSORCIÓN DE AGUA	UNI EN ISO 10545-3	$\leq 0,5\%$	$\leq 0,1\%$	
		 RESISTENZA A ROTTURA BREAKING STRENGTH / RESISTANCE À LA RUPTURE / BRUCHFESTIGKEIT / RESISTENCIA A LA ROTURA	UNI EN ISO 10545-4	$R \geq 35$ N/mm ² $S \geq 700$ N ($< 7,5$ mm) $S \geq 1300$ N ($\geq 7,5$ mm)
 RESISTENZA ABRASIONE PROFONDA (UGL - Matt) DEEP ABRASION RESISTANCE (UGL - Matt) / RÉSISTANCE À L'ABRASION PROFONDE (UGL - Matt) / TIEFENVERSCHLEISSBESTÄNDIGKEIT (UGL - Matt) / RESISTENCIA A LA ABRASIÓN PROFUNDA (UGL - Matt)	UNI EN ISO 10545-6		≤ 175 mm ³	≤ 150 mm ³
	UNI EN ISO 10545-6		dichiarare un valore / declare a value / déclarer une valeur / einen Wert angeben / declarar un valor	-
 RESISTENZA SHOCK TERMICI THERMAL SHOCK RESISTANCE / RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE / WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN / RESISTENCIA A LOS CAMBIOS DE TEMPERATURA	UNI EN ISO 10545-9	resistenza / resistant / résistance / Widerständigkeit / resistencia	TEST DISPONIBILE TEST AVAILABLE / TEST DISPONIBLE / TEST VERFÜGBAR / PRUEBA DISPONIBLE	
		 RESISTENZA AL GELO FROST RESISTANCE / RÉSISTANCE AU GEL / FROSTWIDERSTANDSFÄHIGKEIT / RESISTENCIA AL HIELO	UNI EN ISO 10545-12	resistenza / resistant / résistance / Widerständigkeit / resistencia
 RESISTENZA CHIMICA CHEMICAL RESISTANCE / RÉSISTANCE CHIMIQUE CHEMISCHE BESTÄNDIGKEIT / RESISTENCIA QUÍMICA	UNI EN ISO 10545-13		resistenza / resistant / résistance / Widerständigkeit / resistencia	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
		 RESISTENZA ALLE MACCHIE STAIN RESISTANCE / RÉSISTANCE AUX TACHES / FLECKENFESTIGKEIT / RESISTENCIA A LAS MANCHAS	UNI EN ISO 10545-14	pulibile / cleanable / nettoyable / kann gereinigt werden / lavable
 CLASSIFICAZIONE ANTISDRUCCIOLO ASSESSMENT OF SLIP RESISTANCE / CLASSIFICATION ANTIGLISSE RUTSCHFESTIGKEITSKLASSE / CLASIFICACIÓN ANTIDESLIZANTE	DIN 51130		R	R9 30x30
	DIN 51097	A+B+C	A Natural R9	
	B.C.R.A. (COF)	>0,40 bagnato / wet	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME	
	ANSI A137.1 2012 (DCOF)	>0,42 bagnato / wet	CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME	
	BS 7976- 2:2002 (UK) (Pendulum Test Value)	0-24 scivoloso / slippery / glissant / Rutschig / resbaladizo 25-35 scivolosità moderata / moderately slippery / glissance modérée / mäßige Rutschgefahr / Deslizamiento moderado >36 basso rischio scivolamento / low slipping risk / risque de glissement faible / geringe Rutschgefahr / bajo riesgo de deslizamiento	-	

Piastrelle pressate a secco - Conforme alla norma EN 14411 e ISO 13006 appendice G gruppo B1-a con E $\leq 0,5\%$

Dry pressed tiles - Compliant with standards EN 14411 and ISO 13006 annex G group B1-a with E $\leq 0,5\%$ / Carreau pressé à sec - Conforme à la norme EN 14411 et ISO 13006 annexe G groupe B1-a avec E $\leq 0,5\%$ / Trocken gepresste Fliesen - Erfüllen die Anforderungen der Norm en 14411 und ISO 13006 Anhang g Gruppe B1-a mit E $\leq 0,5\%$ / Baldosas prensadas en seco - Conforme a las normas en 14411 e iso 13006, anexo g grupo B1-a con E $\leq 0,5\%$