












# INFORMAZIONI TECNICHE

TECHNICAL FEATURES / INFORMATIONS TECHNIQUES / TECHNISCHE INFORMATIONEN / INFORMACIÓN TÉCNICA

DESCRIZIONE DESCRIPTION / DESCRIPTION BESCHREIBUNG / DESCRIPCIÓN	NORME REGULATION / NORME / NORM / NORMA	REQUISITI PRESCRITTI REQUIRED VALUES / EXIGENCES RÉGLEMENTAIRES / VORGESCHRIEBENE ANFORDERUNGEN / REQUISITOS ESTABLECIDOS	VALORI VALUES / VALEURS WERTE / VALORES
	EN 14411 - ISO 13006		<b>ECLECTIC</b>
		<p><b>lunghezza-larghezza ±0,3% (±1,0 mm max)</b> <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i></p> <p><b>spessore ±5,0% (±0,5 mm max)</b> <i>thickness / épaisseur / Stärke / espesor</i></p> <p><b>ortogonalità ±0,3% (±1,5 mm max)</b> <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i></p> <p><b>rettilinearità ±0,3% (±0,8 mm max)</b> <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i></p> <p><b>planarità ±0,4% (±1,8 mm max)</b> <i>surface flatness / planéité / Ebenflächigkeit / planaridad</i></p> <p><b>qualità superficie ≥95%</b> <i>surface quality / qualités surface / Oberflächenbeschaffenheit / cualidades superficie</i></p>	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
<b>DIMENSIONI RETTIFICATO</b> SIZES RECTIFIED / FORMAT RECTIFIÉ / ABMESSUNGEN NACH DEM SCHLEIFEN / TAMAÑO RECTIFICADO	UNI EN ISO 10545-2		
		<p><b>lunghezza-larghezza ±0,6% (±2,0 mm max)</b> <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i></p> <p><b>spessore ±5,0% (±0,5 mm max)</b> <i>thickness / épaisseur / Stärke / espesor</i></p> <p><b>ortogonalità ±0,5% (±2,0 mm max)</b> <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i></p> <p><b>rettilinearità ±0,5% (±1,5 mm max)</b> <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i></p> <p><b>planarità ±0,5% (±2,0 mm max)</b> <i>surface flatness / planéité / Ebenflächigkeit / planaridad</i></p> <p><b>qualità superficie ≥95%</b> <i>surface quality / qualités surface / Oberflächenbeschaffenheit / cualidades superficie</i></p>	
<b>DIMENSIONI NON RETTIFICATO</b> SIZES NOT RECTIFIED / FORMAT NON RECTIFIÉ / ABMESSUNGEN VOR DEM SCHLEIFEN / TAMAÑO NO RECTIFICADO	UNI EN ISO 10545-2		
	UNI EN ISO 10545-3	≤0,5%	≤0,1%
<b>ASSORBIMENTO ACQUA</b> WATER ABSORPTION / ABSORPTION D'EAU WASSERAUFNAHME / ABSORCIÓN DE AGUA			
	UNI EN ISO 10545-4	<b>R≥35 N/mm<sup>2</sup></b> <b>S≥700 N (&lt;7,5 mm)</b> <b>S≥1300 N (≥7,5 mm)</b>	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
<b>RESISTENZA A ROTTURA</b> BREAKING STRENGTH / RÉSISTANCE À LA RUPTURE / BRUCHFESTIGKEIT / RESISTENCIA A LA ROTURA			
	UNI EN ISO 10545-6	≤175 mm <sup>3</sup>	≤150 mm <sup>3</sup>
<b>RESISTENZA ABRASIONE PROFONDA (UGL - Matt)</b> DEEP ABRASION RESISTANCE (UGL - Matt) / RÉSISTANCE À L'ABRASION PROFONDE (UGL - Matt) / TIEFENVERSCHLEISSBESTÄNDIGKEIT (UGL - Matt) / RESISTENCIA A LA ABRASIÓN PROFUNDA (UGL - Matt)			
	UNI EN ISO 10545-6	dichiarare un valore / declare a value / déclarer une valeur / einen Wert angeben / declarar un valor	<b>TEST DISPONIBILE</b> TEST AVAILABLE / TEST DISPONIBLE / TEST VERFÜGBAR / PRUEBA DISPONIBLE
<b>RESIST. ABRASIONE SUPERFICIALE (GL - Lappato)</b> SURFACE ABRASION RESISTANCE (GL - Lappato) / RÉSIST. À L'ABRASION SUPERFICIELLE (GL - Rodé) / WIDERSTÄNDIGKEIT GEGEN OBERFLÄCHENVERSCHLEISS (GL - geläppt) / RESIST. ABRASIÓN SUPERFICIAL (GL: esmaltado)			
	UNI EN ISO 10545-9	resistenza / resistant / résistance / Widerständigkeit / resistencia	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
<b>RESISTENZA SHOCK TERMICI</b> THERMAL SHOCK RESISTANCE / RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE / WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN / RESISTENCIA A LOS CAMBIOS DE TEMPERATURA			
	UNI EN ISO 10545-12	resistenza / resistant / résistance / Widerständigkeit / resistencia	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
<b>RESISTENZA AL GELO</b> FROST RESISTANCE / RÉSISTANCE AU GEL / FROSTWIDERSTANDSFÄHIGKEIT / RESISTENCIA AL HIELO			
	UNI EN ISO 10545-13	resistenza / resistant / résistance / Widerständigkeit / resistencia	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
<b>RESISTENZA CHIMICA</b> CHEMICAL RESISTANCE / RÉSISTANCE CHIMIQUE CHEMISCHE BESTÄNDIGKEIT / RESISTENCIA QUÍMICA			
	UNI EN ISO 10545-14	pulibile / cleanable / nettoyable / kann gereinigt werden / lavable	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
<b>RESISTENZA ALLE MACCHIE</b> STAIN RESISTANCE / RÉSISTANCE AUX TACHES / FLECKENFESTIGKEIT / RESISTENCIA A LAS MANCHAS			
	DIN 51130	R	- Lappato 120x278 - 120x120 - 60x120 - 30x120 - 60x60 - 30x60 - Silky 120x278 - 120x120 - 60x120 - 30x120 - 60x60 - 30x60 R9 60x120 - 60x60 - 30x60
<b>CLASSIFICAZIONE ANTISDRUCCIOLO</b> ASSESSMENT OF SLIP RESISTANCE / CLASSIFICATION ANTIGLISSE RUTSCHFESTIGKEITSKLASSE / CLASIFICACIÓN ANTIDESLIZANTE	DIN 51097	A+B+C	- Lappato / - Silky / A Natural R9
	B.C.R.A. (COF)	>0,40 bagnato / wet	<b>CONFORME (NO LAPPATO / SILKY)</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME
	ANSI A137.1 2012 (DCOF)	>0,42 bagnato / wet	<b>CONFORME (NO LAPPATO / SILKY)</b> COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME

Piastrelle pressate a secco - Conforme alla norma EN 14411 e ISO 13006 appendice G gruppo B1-a con E ≤0,5%

Dry pressed tiles - Compliant with standards EN 14411 and ISO 13006 annex G group B1-a with E ≤0,5% / Carreau pressé à sec - Conforme à la norme EN 14411 et ISO 13006 annexe g groupe B1-a avec E ≤0,5% / Trocken gepresste Fliesen - Erfüllen die Anforderungen der Norm en 14411 und ISO 13006 Anhang g Gruppe B1-a mit E ≤0,5% / Baldosas prensadas en seco - Conforme a las normas en 14411 e iso 13006, anexo g grupo B1-a con E ≤0,5%