











INFORMAZIONI TECNICHE

TECHNICAL FEATURES / INFORMATIONS TECHNIQUES / TECHNISCHE INFORMATIONEN / INFORMACIÓN TÉCNICA

| DESCRIZIONE DESCRIPTION / DESCRIPTION BESCHREIBUNG / DESCRIPCIÓN | NORME REGULATION / NORME / NORM / NORMA | REQUISITI PRESCRITTI REQUIRED VALUES / EXIGENCES RÉGLEMENTAIRES / VORGESCHRIEBENE ANFORDERUNGEN / REQUISITOS ESTABLECIDOS | VALORI VALUES / VALEURS WERTE / VALORES |
|---|---|--|---|
| | EN 14411 - ISO 13006 | | PERCORSI SMART |
|  | DIMENSIONI RETTIFICATO SIZES RECTIFIED / FORMAT RECTIFIÉ / ABMESSUNGEN NACH DEM SCHLEIFEN / TAMAÑO RECTIFICADO | UNI EN ISO 10545-2 | <p>lunghezza-larghezza $\pm 0,3\%$ ($\pm 1,0$ mm max) <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i></p> <p>spessore $\pm 5,0\%$ ($\pm 0,5$ mm max) <i>thickness / épaisseur / Stärke / espesor</i></p> <p>ortogonalità $\pm 0,3\%$ ($\pm 1,5$ mm max) <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i></p> <p>rettilinearità $\pm 0,3\%$ ($\pm 0,8$ mm max) <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i></p> <p>planarità $\pm 0,4\%$ ($\pm 1,8$ mm max) <i>surface flatness / planéité / Ebenflächigkeit / planaridad</i></p> <p>qualità superficie $\geq 95\%$ <i>surface quality / qualités surface / Oberflächenbeschaffenheit / cualidades superficie</i></p> |
| | DIMENSIONI NON RETTIFICATO SIZES NOT RECTIFIED / FORMAT NON RECTIFIÉ / ABMESSUNGEN VOR DEM SCHLEIFEN / TAMAÑO NO RECTIFICADO | UNI EN ISO 10545-2 | <p>lunghezza-larghezza $\pm 0,6\%$ ($\pm 2,0$ mm max) <i>length-width / longueur-largeur / Länge-Breite / longitud-ancho</i></p> <p>spessore $\pm 5,0\%$ ($\pm 0,5$ mm max) <i>thickness / épaisseur / Stärke / espesor</i></p> <p>ortogonalità $\pm 0,5\%$ ($\pm 2,0$ mm max) <i>rectangularity / orthogonalité / Rechtwinkligkeit / ortogonalidad</i></p> <p>rettilinearità $\pm 0,5\%$ ($\pm 1,5$ mm max) <i>straightness / rectilignité / Geradlinigkeit / rectilineidad</i></p> <p>planarità $\pm 0,5\%$ ($\pm 2,0$ mm max) <i>surface flatness / planéité / Ebenflächigkeit / planaridad</i></p> <p>qualità superficie $\geq 95\%$ <i>surface quality / qualités surface / Oberflächenbeschaffenheit / cualidades superficie</i></p> |
|  | ASSORBIMENTO ACQUA WATER ABSORPTION / ABSORPTION D'EAU WASSERAUFNAHME / ABSORCIÓN DE AGUA | UNI EN ISO 10545-3 | $\leq 0,5\%$ $\leq 0,1\%$ |
|  | RESISTENZA A ROTTURA BREAKING STRENGTH / RÉSISTANCE À LA RUPTURE / BRUCHFESTIGKEIT / RESISTENCIA A LA ROTURA | UNI EN ISO 10545-4 | R≥ 35 N/mm² S≥ 700 N (<7,5 mm) S≥ 1300 N ($\geq 7,5$ mm) CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |
|  | RESISTENZA ABRASIONE PROFONDA (UGL - Matt) DEEP ABRASION RESISTANCE (UGL - Matt) / RÉSISTANCE À L'ABRASION PROFONDE (UGL - Matt) / TIEFENVERSCHLEISSBESTÄNDIGKEIT (UGL - Matt) / RESISTENCIA A LA ABRASIÓN PROFUNDA (UGL - Matt) | UNI EN ISO 10545-6 | ≤ 175 mm ³ ≤ 150 mm³ |
|  | RESIST. ABRASIONE SUPERFICIALE (GL - Lappato) SURFACE ABRASION RESISTANCE (GL - Lappato) / RÉSIST. À L'ABRASION SUPERFICIELLE (GL - Rodé) / WIDERSTÄNDIGKEIT GEGEN OBERFLÄCHENVERSCHLEISS (GL - geläppt) / RESIST. ABRASIÓN SUPERFICIAL (GL: esmaltado) | UNI EN ISO 10545-6 | dichiarare un valore / declare a value / déclarer une valeur / einen Wert angeben / declarar un valor |
|  | RESISTENZA SHOCK TERMICI THERMAL SHOCK RESISTANCE / RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE / WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN / RESISTENCIA A LOS CAMBIOS DE TEMPERATURA | UNI EN ISO 10545-9 | resistenza / resistant / résistance / Widerständigkeit / resistencia CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |
|  | RESISTENZA AL GELO FROST RESISTANCE / RÉSISTANCE AU GEL / FROSTWIDERSTANDSFÄHIGKEIT / RESISTENCIA AL HIELO | UNI EN ISO 10545-12 | resistenza / resistant / résistance / Widerständigkeit / resistencia CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |
|  | RESISTENZA CHIMICA CHEMICAL RESISTANCE / RÉSISTANCE CHIMIQUE CHEMISCHE BESTÄNDIGKEIT / RESISTENCIA QUÍMICA | UNI EN ISO 10545-13 | resistenza / resistant / résistance / Widerständigkeit / resistencia CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |
|  | RESISTENZA ALLE MACCHIE STAIN RESISTANCE / RÉSISTANCE AUX TACHES / FLECKENFESTIGKEIT / RESISTENCIA A LAS MANCHAS | UNI EN ISO 10545-14 | pulibile / cleanable / nettoyable / kann gereinigt werden / lavable CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |
| | | DIN 51130 | R R9 60x60 - 40x60 - 30x60 - 20x60 R11 120x240 K2 - 30x240 K2 - 120x120 K2 - 45x90 K2 - 60x60 - 60x60 K2 - 60x60 K3 - 40x60 - 30x60 - 20x60 - 15x30 N.RT |
|  | CLASSIFICAZIONE ANTISDRUCCIOLO ASSESSMENT OF SLIP RESISTANCE / CLASSIFICATION ANTIGLISSE RUTSCHFESTIGKEITSKLASSE / CLASIFICACIÓN ANTIDESLIZANTE | DIN 51097 | A+B+C A Natural R9 / A+B+C Structured R11 |
| | | B.C.R.A. (COF) | >0,40 bagnato / wet CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |
| | | ANSI A137.1 2012 (DCOF) | >0,42 bagnato / wet CONFORME COMPLIANT / CONFORME ANFORDERUNGEN ERFÜLLT / CONFORME |

Piastrelle pressate a secco - Conforme alla norma EN 14411 e ISO 13006 appendice G gruppo B1-a con E $\leq 0,5\%$

Dry pressed tiles - Compliant with standards EN 14411 and ISO 13006 annex G group B1-a with E $\leq 0,5\%$ / Carreau pressé à sec - Conforme à la norme EN 14411 et ISO 13006 annexe g groupe B1-a avec E $\leq 0,5\%$ / Trocken gepresste Fliesen - Erfüllen die Anforderungen der Norm en 14411 und ISO 13006 Anhang g Gruppe B1-a mit E $\leq 0,5\%$ / Baldosas prensadas en seco - Conforme a las normas en 14411 e iso 13006, anexo g grupo B1-a con E $\leq 0,5\%$