







INFORMAZIONI TECNICHE  
TECHNICAL FEATURES / INFORMATIONS TECHNIQUES / TECHNISCHE INFORMATIONEN / INFORMACIÓN TÉCNICA

DESCRIZIONE DESCRIPTION / DESCRIPTION BESCHREIBUNG / DESCRIPCIÓN	NORME REGULATION / NORME / NORM / NORMA  EN 14411 - ISO 13006	REQUISITI PRESCRITTI REQUIRED VALUES / EXIGENCES RÉGLEMENTAIRES / VORGESCHRIEBENE ANFORDERUNGEN / REQUISITOS ESTABLECIDOS	VALORI VALUES / VALEURS WERTE / VALORES
 <b>DIMENSIONI RETTIFICATO</b> SIZES RECTIFIED / FORMAT RECTIFIÉ / ABMESSUNGEN NACH DEM SCHLEIFEN / TAMAÑO RECTIFICADO	UNI EN ISO 10545-2	lunghezza-larghezza ±0,3% (±1,0 mm max) lenght-width / longueur-largeur / Länge-Breite / longitud-ancho	-
		spessore ±5,0% (±0,5 mm max) thickness / épaisseur / Stärke / espesor	
		ortogonalità ±0,3% (±1,5 mm max) rectangularity / orthogonali�� / Rechtwinkligkeit / ortogonalidad	
		rettilinearit�� ±0,3% (±0,8 mm max) straightness / rectilignit�� / Geradlinigkeit / rectilineidad	
		planarit�� ±0,4% (±1,8 mm max) surface flatness / plan����� / Ebenfl��chigkeit / planaridad	
 <b>DIMENSIONI NON RETTIFICATO</b> SIZES NOT RECTIFIED / FORMAT NON RECTIFI�� / ABMESSUNGEN VOR DEM SCHLEIFEN / TAMA��O NO RECTIFICADO	UNI EN ISO 10545-2	lunghezza-larghezza ±0,6% (±2,0 mm max) lenght-width / longueur-largeur / L��nge-Breite / longitud-ancho	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERF��LLT / CONFORME
		spessore ±5,0% (±0,5 mm max) thickness / ��paisseur / St��rke / espesor	
		ortogonalit�� ±0,5% (±2,0 mm max) rectangularity / orthogonali�� / Rechtwinkligkeit / ortogonalidad	
		rettilinearit�� ±0,5% (±1,5 mm max) straightness / rectilignit�� / Geradlinigkeit / rectilineidad	
		planarit�� ±0,5% (±2,0 mm max) surface flatness / plan����� / Ebenfl��chigkeit / planaridad	
 <b>ASSORBIMENTO ACQUA</b> WATER ABSORPTION / ABSORPTION D'EAU WASSERAUFNAHME / ABSORCI��N DE AGUA	UNI EN ISO 10545-3	≤0,5%	≤0,1%
		<b>RESISTENZA A ROTTURA</b> BREAKING STRENGHT / R��SISTANCE �� LA RUPTURE / BRUCHFESTIGKEIT / RESISTENCIA A LA ROTURA	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERF��LLT / CONFORME
		UNI EN ISO 10545-4	
		<b>RESISTENZA ABRASIONE PROFONDA (UGL - Matt)</b> DEEP ABRASION RESISTANCE (UGL - Matt) / R��SISTANCE �� L'ABRASION PROFONDE (UGL - Matt) / TIEFENVERSCHLEISSBEST��NDIGKEIT (UGL - Matt) / RESISTENCIA A LA ABRASI��N PROFUNDA (UGL - Matt)	
		UNI EN ISO 10545-6	
 <b>RESIST. ABRASIONE SUPERFICIALE (GL - Lappato)</b> SURFACE ABRASION RESISTANCE (GL - Lappato) / R��SIST. �� L'ABRASION SUPERFICIELLE (GL - Rod��) / WIDERST��NDIGKEIT GEGEN OBERFL��CHENVERSCHLEISS (GL - gel��ppt) / RESIST. ABRASI��N SUPERFICIAL (GL: esmaltado)	UNI EN ISO 10545-6	dichiarare un valore / declare a value / d��clarer une valeur / einen Wert angeben / declarar un valor	-
		UNI EN ISO 10545-9	
		<b>RESISTENZA SHOCK TERMICI</b> THERMAL SHOCK RESISTANCE / R��SISTANCE AUX ��CARTS DE TEMP��RATURE / WIDERSTANDSF��HIGKEIT GEGEN TEMPERATURSCHWANKUNGEN / RESISTENCIA A LOS CAMBIOS DE TEMPERATURA	
		UNI EN ISO 10545-12	
		<b>RESISTENZA AL GELO</b> FROST RESISTANCE / R��SISTANCE AU GEL / FROSTWIDERSTANDSF��HIGKEIT / RESISTENCIA AL HIELO	
 <b>RESISTENZA CHIMICA</b> CHEMICAL RESISTANCE R��SISTANCE CHIMIQUE CHEMISCHE BEST��NDIGKEIT RESISTENCIA QU��MICA	UNI EN ISO 10545-13	resistenza / resistant / r��sistance / Widerst��ndigkeit / resistencia	<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERF��LLT / CONFORME
		UNI EN ISO 10545-14	
		<b>RESISTENZA ALLE MACCHIE</b> STAIN RESISTANCE / R��SISTANCE AUX TACHES / FLECKENFESTIGKEIT / RESISTENCIA A LAS MANCHAS	
		UNI EN ISO 10545-14	
		pulibile / cleanable / nettoyyable / kann gereinigt werden / lavable	
 <b>CLASSIFICAZIONE ANTISDRUCCIOLO</b> ASSESSMENT OF SLIP RESISTANCE / CLASSIFICATION ANTIGLISSE RUTSCHFESTIGKEITSKLASSECLASIFICACI��N ANTIDESLIZANTE	DIN 51130	R	R11 30x30 N.RT
		DIN 51097	A+B+C
		B.C.R.A. (COF)	>0,40 bagnato / wet
		ANSI A137.1 2012 (DCOF)	>0,42 bagnato / wet
			<b>CONFORME</b> COMPLIANT / CONFORME ANFORDERUNGEN ERF��LLT / CONFORME

Piastrelle pressate a secco - Conforme alla norma EN 14411 e ISO 13006 appendice G gruppo B1-a con E ≤0,5%  
Dry pressed tiles - Compliant with standards EN 14411 and ISO 13006 annex G group B1-a with E ≤0,5% / Carreau press      sec - Conforme    la norme EN 14411 et ISO 13006 annexe g groupe B1-a avec E ≤0,5% / Trocken gepresste Fliesen - Erf  llen die Anforderungen der Norm en 14411 und ISO 13006 Anhang g Gruppe B1-a mit E ≤0,5% / Baldosas prensadas en seco - Conforme a las normas en 14411 e iso 13006, anexo g grupo B1-a con E ≤0,5 %